

Emerging Designs and Developments of Biodegradable Metallic Alloys for Biomedical Applications

UBAH Promise Chima¹, Musa Yahaya Abubakar², Anidobu Clara Obianuju³, Khalil Nazir Abdullahi³, Saidu Bello Mamudu³

¹Department of Chemistry, Federal university of Technology Akure

²Department of Industrial Chemistry, Federal university Wukari Taraba state


³Department of Chemistry, Federal university Wukari Taraba state

Corresponding Author: musayahaya@fuwukari.edu.ng

Received: 14th May 2026; Revised: 25th May 2026; Accepted: 05th Jun 2026

Abstract: Biodegradable metal alloys are new classes of biomaterials that can offer mechanical support that will dissolve in the human body after the therapeutic regime. Alloy implants made from magnesium, zinc and iron will have more advantages than conventional ones as they do not present long term side effects. Also, they will not require removal. This study explains recent findings, designs and constructions of metal alloys that are highly biodegradable for temporary purposes. Welders of materials beneath human skin must certainly be familiar with each of these properties: corrosion house, integrity, biocompatibility. Research shows that your body responds quickly to natural elements, helping performance and recovery. We include antioxidants and growth problem solvers. We have updated the breakdown systems and your human response. Apart from that, new applications can arise in injections, arthritis, and heart and tissue repair. All of these methods require careful timing to function correctly. While having known alloys presents great issues for material outcome and "degradation" of parts, the challenges continue. Hospitals can use biodegradable metallic alloys, which allow for the use of advanced materials for the transfer from lab study to common practice.

Graphical Abstract



Keywords: Biodegradable, alloys, magnesium-based systems, biomedical applications.

How to cite this article: Ubah PC, Abubakar MY, Anidobu CO, Abdullahi KN, Mamudu SB. Emerging designs and developments of biodegradable metallic alloys for biomedical applications. NextGen Chem Discov. 2026 Apr-Jun;2(2):1-19.

Conflict of interest: None

Introduction

The medical implants technology innovations has impacted the healthcare sector and saved million lives worldwide and growing. Metallic implants have been essential in orthopedic, cardiovascular, and craniofacial reconstruction due to their mechanical strength and durability. Conventional metallic implants are indeed advantageous and widely used but the permanence of these implants (which commonly consist of stainless steel, cobalt-chromium and titanium alloys) also leads to multiple physiological and clinical complications that limit their long-term success [1]. Because these materials cannot degrade or be resorbed, they need secondary surgical removal. This causes greater chances of infection, inflammatory response, and high health-care costs [2; 3]. These implants have an elastic moduli that is far superior to bone But) it results in mechanical mismatch. The stress shielding and subsequent bone resorption affect the osseointegration and stability of the implant.

The urgent demand now is for biodegradable metallic implants (BMIs), fundamentally advanced materials which can impart mechanical support during the healing phase and subsequently cease to exist in the body. Medical materials science essentially aims to develop engineered materials that can be successfully transplanted into the human body. Magnesium based alloys are one of the potential candidate materials, which came under increased attention due to their mechanical properties which are similar to those of human bone. Moreover, alloys found in the human body have shown to have a positive biological impact on osteogenesis as well as angiogenesis [4; 5]. Researchers think that, unlike a permanent metallic implant which becomes a permanent foreign object in the body, magnesium could be a better bet [1]

However, biodegradable metallic systems possess several significant challenges that prevent their successful clinical translation. The main challenge is to achieve degradation kinetics that align with tissue healing rates [6]. If the degradation is too fast, mechanical failure may occur, and hydrogen gas can accumulate around the site of the implant. Conversely, a degradation process that is too slow may lead to long-term foreign-body exposure, which is counter to the biodegradability of the materials [7]. So, it is essential to control the loss of quality so that the structure remains intact during the healing phase. It will surely undergo complete resorption thereafter. Balancing these competing requirements necessitates an integrated understanding of material composition, electrochemical stability, and local biological interactions in the implantation environment [8].

Another key issue is mechanical stability as well as degradation control. The implant should be able to carry an adequate load while healing, similar to bone tissue. Although magnesium is a good biocompatible and biodegradable material, it has a low yield strength and is likely to undergo stress corrosion cracking in physiological environments [6]. To overcome these shortcomings, alloying elements such as calcium, zinc, and manganese can be added at specific levels to improve strength, corrosion resistance, and microstructural uniformity [4]. These changes not only provide stability to the mechanical properties but also influence the morphology of corrosion and patterns of ion release, which are critical to biological compatibility during degradation. The biological performance of biodegradable metallic implants is also decisively determined by their surface characteristics. The initial protein adsorption, initial cell adhesion, and subsequent tissue integration are determined by the interface between the surface of the implant and the surrounding biological environment. When bone cells stay on and grow on the surface of an implant

(osseointegration), there is mechanical anchorage as well as healing at an ideal speed. Also, surface engineering can support that ideal osseointegration.

On the other hand, poorly designed surfaces can generate an inflammatory response or bacterial colonization, leading to the rejection or infection of implants. According to [9] Recent advancements in surface modification techniques such as plasma electrolytic oxidation, anodization, and hydroxyapatite coating are effective at enhancing corrosion resistance and promoting osteoblast proliferation [8]. Similarly, customized surface roughness, porosity, and surface energy through chemical and physical treatments create a bioactive interface simulating the natural bone microenvironment.

Both polymers and ceramics have been researched as biodegradable materials for some time now, but they do not offer enough mechanical strength for use in load-bearing applications [1]. Durability degradation of polymeric materials into acidic by-products can cause local inflammation and pH imbalance. Although ceramics are biocompatible, they are brittle and inflexible for applications in dynamic biological systems. Unlike the options above, biodegradable metallic alloys provide both strength and adaptability, which biological mechanisms can trigger. Thus, they can be deployed into wide-ranging applications, including orthopedic, cardiovascular, and maxillofacial usages [10; 11]. Magnesium-based implants are similar to cortical bone in terms of structure. They would therefore be expected to maintain biomechanical compatibility and stress shielding (which refers to the decrease in bone density that occurs near metallic implants) [12]. Long-term use of biodegradable alloys may offer support in load distribution and stimulate osteogenesis for better physiological response. A key area of research here involves decoding and manipulating the corrosion mechanisms that cause degradation in physiological environments. The alloy's microstructure, surface film formation, and ionic composition together govern the corrosion mechanisms and rates of degradation of the alloy. Magnesium dissolves in metal construction, producing hydrogen and magnesium hydroxide. The presence of $Mg(OH)_2$ has a temporary inhibitory effect, but the addition of chloride ions from body fluids disrupts this layer, resulting in accelerated degradation. [6,8]. So, to achieve predictably uniform degradation, the material design strategies should ensure microstructural homogeneity, the distribution of grain boundaries, and the stability of the passive film. In the work of [7], advanced characterization techniques such as electrochemical impedance spectroscopy, X-ray diffraction, and *in vivo* imaging are increasingly being applied. When designing biodegradable implants, to achieve a controlled degradation rate that aligns with the timeline of tissue restoration is mostly considered, as depicted in Figure 1. The degradation rate can be regulated by selecting appropriate alloying elements. Incorporating these elements enhances degradation or corrosion resistance up to a certain threshold, beyond which the resistance will decline and controlled failure will progress [13]. Magnesium (Mg) alloys are among the materials employed for biodegradable purposes.




Figure 1: Degradation process for biodegradable Magnesium implant.

There are many innovations in surface engineering in recent times, which hold great promise for simultaneous corrosion control and biointegration. The addition of bioactive ceramics like hydroxyapatite or bio-glass in coatings can prevent corrosion and enhance bone bonding due to their osteoconductive surface. Likewise, polymer coatings that are modified with therapeutic or anti-bacterial agents offer controlled drug release and resistance to infection. These multilayer coatings convert implants from passive supports to active biological interfaces that modulate cellular behavior and promote healing. The addition of nanostructured or hierarchical surfaces to biodegradable metals enhances the surface area-to-volume ratio of these materials, improving their interaction with cells and promoting tissue regeneration [9]. The world is moving towards personal and regenerative medicine, which creates demand for materials that respond to individual patients. The changing composition and mechanical properties of biodegradable metals serve the purpose well. The merging of additive manufacturing (3D printing) allows for patient-specific implants with complex geometries that imitate natural bone architectures, enhancing further functional outcomes [4]. Examples of such approaches bring together materials science, bioengineering, and clinical engineering as credible candidates for next-generation biomedical implants. Even with the innovations, achieving widespread clinical penetration is difficult. Testing and regulations should change to allow for biodegradable systems that can degrade at different rates over time. The growing healthcare needs of aging populations and trauma cases are critical. So, collaboration is essential. Interdisciplinary cooperation between material scientists, engineers, and clinicians is vital to translate laboratory breakthroughs into real-world solutions.

This study aims to investigate the current status of biodegradable metallic implants, focusing on material innovations and performance optimisation to balance degradation kinetics, mechanical stability, and biocompatibility. By reviewing material design, surface modification, and biological integration, this study identifies promising pathways toward next-generation biodegradable implants with clinical safety, functional reliability, and regenerative capacity for medical applications in the global health market.

Method

Research Design

This study adopted a systematic review and analytical synthesis approach to examine recent advances in biodegradable metallic alloys, with particular emphasis on their biocompatibility, degradation kinetics, and functional performance in biomedical implants. The research design integrates quantitative data interpretation and qualitative content analysis drawn from peer-reviewed publications, laboratory reports, and experimental case studies. The approach was chosen to ensure a comprehensive evaluation of existing scientific evidence and to identify key gaps guiding future material innovation.

Data Sources and Selection Criteria

Relevant scholarly materials were retrieved from reputable databases, including ScienceDirect, PubMed, SpringerLink, and Scopus, covering the period 2015–2025. Search keywords included "biodegradable metal implants," "magnesium alloys," "zinc-based biomaterials," and "surface modification of bio-metals."

Publications were screened based on the following inclusion criteria:

Studies focused on biodegradable metallic systems applied in orthopedic or cardiovascular contexts are ongoing.

Data Extraction and Analytical Approach

Data extraction involved identifying and categorizing information under key themes: composition of alloys, fabrication and processing routes, corrosion mechanisms, and biological interactions. Quantitative data such as degradation rates, tensile strength, and ion release profiles were tabulated and compared across alloy systems. A comparative matrix analysis was employed to synthesize trends among Mg-, Zn-,

and Fe-based biodegradable alloys, highlighting the correlation between material composition, surface modification strategies, and in-vitro/in-vivo behavior.

Validation and Reliability

To ensure methodological reliability, multiple reviewers independently verified extracted data to minimize bias. Consistency checks were conducted using cross-referencing of experimental results and citation triangulation. The study adhered to PRISMA guidelines (Preferred Reporting Items for Systematic Reviews and Meta-Analyses) for transparency and reproducibility.

Ethical Considerations

Although this research relied primarily on secondary data, all referenced materials were sourced from open-access or institutionally licensed databases, with appropriate citation and acknowledgement to preserve academic integrity. Ethical compliance followed the Committee on Publication Ethics (COPE) framework for responsible research reporting.

Principles of Biodegradable Metallic Alloys

The first principle of biodegradable metals is to control electrochemical dissolution so that the degradation occurs predictably and biologically acceptably [14]. Biodegradable alloys are made to dissolve in physiological media. Like the absorption of salt or minerals, they dissolve, allowing a regular metabolism to take over. The magnesium ions released during degradation play key roles in cellular signaling and bone mineralization, making them tolerable and even therapeutically beneficial [15; 16]. The alloy composition, microstructure, and surface properties of such materials influence their degradation behavior. By adding magnesium with elements such as calcium, zinc, and rare earth elements, it can change the grain size and corrosion potential. The dissolution rate is compatible with tissue regeneration [17]. Surface Treatments passivate or reduce local corrosion while mechanical stability is ensured during healing. So, the main issue to conquer while designing the biodegradable metal is this balance – strong enough for the tissue yet weak enough to fade away.




Figure 2: Schematic Illustration of Biodegradable Scaffold Degradation and Tissue Healing Process

Electrochemical Dissolution in Physiological Environments

Biodegradable metals break down in living subjects due to electrochemical reactions at the metal surface's interfacial region and the physiological lifecycle. The environment has a significant influence on the response, especially the pH, ionic strength, temperature, and protein adsorption [6]. For magnesium-based implants, degradation commences when the metal reacts with water molecules to form magnesium hydroxide and hydrogen gas. The formation of this hydroxide layer offers temporary protection, but it is easily disrupted in the presence of chloride ions found in physiological fluids [8]. If the degradation happens too fast, hydrogen gas may build up in the area near an implant. Although less common, this may cause subcutaneous gas pockets or embolism [19]. Additionally, [20] showed that an increase in local alkalinity, which occurs due to the formation of hydroxide, may disrupt cell metabolism and impede

osteogenesis. So, electrochemical optimization aims not at corrosion prevention, but at corrosion regulation, that is, maintaining functional performance until tissue integration occurs. Researchers carry out surface engineering and tuning of composition. The metal surface is exposed to harsh ions when a metal coating is used. Surface coatings like Hydroxyapatite (HA) or polymer films create diffusion barriers. They are helpful to the implant surface.

The addition of new elements, such as zinc and calcium, achieves a more uniform corrosion with less pitting [21]. It has also been argued that this new composition reduces allergic reactions and improves biocompatibility. Not only chlorides but also other physiologically relevant ions, such as phosphates, sulfates, and carbonates, can interact with metallic ions during corrosion. These can help form complex compounds, which stabilize or accelerate degradation depending on the local electrochemical balance [22]. By studying these interactions at the microscopic level, it becomes possible to design alloys that can dissolve predictively in nature.

Degradation for Tissue Healing

To function correctly, biodegradable implants should have kinetics that match the tissue regeneration rates. In an ideal situation, a prosthesis has mechanical stability at the beginning of the healing phase and gradually transfers stress to the regenerating bone through degradation [29]. If the degradation occurs too quickly, the structure can lose strength before complete healing has taken place, and this can cause collapse or nonunion. On the other hand, slow degradation allows remaining portions to hamper tissue remodeling and induce inflammation [23].

The microstructure of the alloy plays a key role in determining degradation kinetics. Uniform corrosion is seen with fine-grained structures having homogeneous phase distribution. Pitting or localized corrosion is seen with heterogeneous structures. Furthermore, environmental factors, including mechanical forces, fluid movement, and pH, add complexity to the degradation process. Stress or cyclic loading can lead to microcracks that promote anodic sites for localized corrosion under stress [24]. Controlled degradation also enables gradual load transfer from an implant to its surrounding bone, leading to bone remodeling through mechano transduction pathways. In contrast, sudden loss of support or uneven degradation may set off micro-instabilities that damage osteointegration. So, knowledge of materials science and biomechanics must be integrated so that the degradation kinetics complement natural healing and not interfere with it.

Thermodynamics and Kinetics of Corrosion Processes

The thermodynamic stability and kinetic control dictate the corrosion behavior of biodegradable metals. Thermodynamics determines the favorability of the corrosion reactions. The kinetics determine how fast the corrosion reactions occur under physiological conditions [6]. The Pourbaix diagram is an example of how regular tools can make theoretical predictions about the stability of metals. The diagram shows ranges of pH and potential, indicating whether the passive film would form or dissolve. In biological systems, in reality, corrosion rates differ from thermodynamic predictions due to kinetic barriers like diffusion limitations, protein adsorption, and complexing agents [25].

Magnesium and zinc alloys create an oxide or hydroxide layer that temporarily prevents corrosion, but this layer breaks down as chloride ions attack it, causing localized pitting [26]. The stability of these films depends on their alloy composition and microstructure. Zinc systems have longer reaction times, which makes them applicable where long-term structure is needed [7]. It is essential to be able to predict the *in vivo* degradation patterns of new alloys. Furthermore, understanding thermodynamic feasibility and kinetic control will help scientists design alloys.

Biodegradable metallic alloys are formed by combining relevant principles from electrochemistry, materials design, and biological integration into a transformative idea: temporary function with lasting

healing. These alloys help the body during recovery and later vanish without leaving any foreign material behind. To achieve this ideal, precise control of electrochemical dissolution, degradation kinetics, and corrosion thermodynamics is required for a predictable, safe, and effective performance. Magnesium based alloys are leading because of their biocompatibility, biofunctionality, and bone-like mechanical properties. Though corrosion control and hydrogen evolution continue to pose a challenge, inspired solutions have been developed [28;5]. Biodegradable implant technology will progress through alloy engineering, surface modification, and kinetic modeling, ensuring the sound degradation of devices in sync with tissue healing.

Classes of Biodegradable Metallic Alloys

Biodegradable metallic alloys are a new class of biomaterials that combine the mechanical properties of metals with the resorption characteristics of degradable systems. The primary purpose of these materials is to give temporary mechanical support during tissue healing. Then they degrade into biologically safe products that are either absorbed or excreted by the body. The research on these alloys has focused on corrosion resistance, degradation kinetics, and bioactivity, all without compromising mechanical integrity and biological compatibility [28]

Table 2: Effect of alloying elements on Mg alloy performance [6]

Alloying Elements	Biocompatibility	Corrosion Resistance	Mechanical Performance
Al	Al is neurotoxic. It can cause Alzheimer's disease and damage muscle fibers.	It is beneficial in providing corrosion resistance	Increases strength and plasticity.
Zn	Non-cytotoxic and good biocompatibility.	Corrosion resistance decreases with higher Zn content.	Zn participates in solid solution strengthening, increasing strength with increasing Zn content.
Mn	Cytotoxic and neurotoxic.	Provide good corrosion resistance	It gives higher yield strength and reduces tensile strength and ductility.
Ca	An essential component of human bone.	Corrosion resistance decreases with increasing Ca content.	With increasing Ca content, strength increases, and plasticity decreases.
Sr	Sr is a vital component of human bone. It also aids in bone formation.	Corrosion resistance of Mg alloy drops with increasing Sr content.	The strength of the alloy increases with increasing Sr content.
Zr	Good biocompatibility and bone-bonding ability.	Corrosion resistance decreases with increasing Zr content.	Grains undergo refinement, increasing strength and plasticity
Nd	Cytotoxic at high concentrations but has good biosafety at low concentrations.	Improves corrosion resistance	Forms new phases, grain refinement, and improvement in mechanical performance

In biomedical research, three metallic systems were primarily investigated: magnesium-based, zinc-based, and iron-based alloys, due to their excellent mechanical properties and varying degradation characteristics [5,4]. Each type of alloy has its own electrochemical activity, microstructure, and biological behaviour. This means that each alloy is suitable for different applications. The alloy systems are studied in detail concerning their intrinsic characterisation, corrosion mechanisms, and biological responses, and they also encompass updated scientific knowledge relevant to these metals.

Magnesium Based Alloys. (Lightweight Strength and Controlled Bioabsorption)

The most promising biodegradable metallic biomaterials for orthopedic and cardiovascular applications are magnesium-based alloys. Magnesium has an elastic modulus (41–45 GPa) similar to that of natural bone, resulting in less stress shielding, which is the resorption of bone around stiff implants due to mechanical mismatch [4]. Due to its mechanical compatibility, the physiological loads are transmitted naturally, stimulating osteogenesis and improving the remodeling process [5].




Figure 3: Sol-gel coating process. For Mg alloy implants, the object would be subjected to dip coating or electro-deposition.

One of the main challenges associated with magnesium and its compounds is their high susceptibility to corrosion and hydrogen gas evolution in physiological environments. [18]. When it comes into contact with bodily fluids, magnesium reacts with water to produce magnesium hydroxide and hydrogen. The hydroxide layer is initially protective, but chloride ions from biological fluids dissolve this layer, causing corrosion. When too much hydrogen builds up, it can form pockets under the skin. These interfere with tissue attachment. Careful mixing of metals and modifying surfaces can lower this risk [21]. Magnesium is frequently alloyed with calcium, zinc, and manganese to fine-tune its degradation kinetics, or with rare earth elements to achieve a refined grain structure and create intermetallic phases that hinder corrosion [14]. The addition of substances, such as hydroxyapatite, fluorides, and biodegradable polymers as surface coatings, improves the predictability of their resorption by establishing diffusion barriers.

Table 1: Mechanical Properties of different Magnesium alloys and non-biodegradable materials [30]

Material	Young's (GPa)	Modulus	Yield (MPa)	Strength	Tensile (MPa)	Strength	Hardness (HB)
Ti-6Al-4V	55-110		760-1103		860-965		334
Co-Cr	240		500-1500		900-1540		
Stainless Steel	200		170-310		540-1000		201
Magnesium	45		-		170		
AZ31	45		171-176		290		49
AZ91	45		160		240		63
Mg-Ca-Zn	45				-		30-60

Magnesium ions support cellular metabolism and enzyme activation, and they also assist in the mineralization of bones. Southwestern University scientists applied ideas of non Crystalline materials to the transient, particle-bound nature of water, a model for the formelian crystal less metal, in 2018. The Amplitude published an interesting article. Also, magnesium degradation elements are non-toxic materials found in cells and used for structure and metabolism.

Though advantageous, the task of balancing mechanical stability with corrosion rate persists. If degradation occurs too fast, mechanical failure will happen before it should, while slight degradation will delay the bioresorption of the device. Research is actively working toward this balance through microstructural optimization, nanostructured coatings, and AI-assisted alloy design. It is expected that magnesium could help in staying ahead in biodegradable metals

Zinc-Based Alloys, Balanced Degradation and Biofunctionality

Biodegradable metals, particularly the subsequent generation of zinc-based alloys with a moderate corrosion rate and a broad antimicrobial spectrum, are gaining interest [23]. Zinc corrodes at a regulated rate, unlike magnesium, which often degrades quickly. Therefore, zinc is more suitable for tissue regeneration. Because of this, zinc alloys are especially notable when it comes to vascular stents, wound fixation devices, and bioresorbable screws that will need mechanical support over a few months [31]. The nature of Zinc corrosion is that zinc oxidizes to zinc oxide. This ensures a gradual dissolution. Although the passivation film doesn't resist corrosion optimally in a chloride-rich environment, it offers more stable corrosion resistance compared to magnesium in the same physiological environment [28]. Zinc deteriorates slowly. This means that risks of gas formation or local alkalinization are low. Thus, cytocompatibility and tissue integration are better.

Alloying is one of the most essential tools to optimize the properties of zinc. Magnesium type additions that include calcium, manganese, and silver improve strength and corrosion resistance through grain refinement and the formation of stable intermetallic [32]. By including silver or copper, antimicrobial activity is maximized, thereby minimizing the chances of post-surgical infection, which is quite beneficial for medical devices exposed to such environments.

Varied release of Zn^{2+} exerts osteoblast and fibroblast growth stimulation and antibacterial effects on surrounding tissues [5]. Zinc is tolerated physiologically and incorporated into proteins such as carbonic anhydrase and alkaline phosphatase. It is biologically compatible and has a long-term degradation in the body. Although pure zinc has a yield strength of ≈ 100 MPa, this is no match for magnesium or iron alloys. Researchers are developing zinc alloys with microstructures that have a crystal direction preference so the material degrades in specific orientations, e.g., along the implant geometry and stress lines. Zinc-based

materials will have moderate degradation rates, amino acid stability, biological functionality, chemical stability, and corrosion ability, which make them promising biomaterials for many clinical applications [28; 33].

Iron-Based Alloys. Strength, Stability, and Slow Resorption

According to [6], iron-based alloys are the oldest and strongest biodegradable metallic systems with excellent mechanical strength and ductility. Due to their mechanical properties, including the yield strength of more than 200 MPa and tensile strengths often exceeding 400 MPa, they are suitable for applications involving high loads, such as bone plates and cardiovascular scaffolds [26]. The most significant disadvantage of iron is that it degrades very slowly in physiological conditions. When iron corrodes, it creates an insoluble layer of iron oxides and hydroxides. This layer is compact and forms on the surface of the metal. It prevents any further dissolution of the iron. The durability of the structure is assured by self-passivation, but complete bioresorption can take years in some cases, extending well beyond the healing period [34].

Researchers have tried many modification strategies to get over this. Mixing iron with other elements causes uniform corrosion of steel due to the failure to form a passive layer. Instead, porous microstructures and micro-galvanic coupling with more active metals like zinc or magnesium hasten degradation by allowing ionic diffusion and electrolyte penetration [14]. Biologically, iron is helpful for the transport of oxygen, cell respiration, and enzyme catalysis. Thus, its metabolic by-products are generally tolerated well. Despite that, an overabundance of Fe^{2+} ions can lead to oxidative stress and inflammation, making it necessary to control the kinetics of degradation. Recent research suggests nanoscale coatings and laser texturing can tune dissolution rates, making iron-based systems more predictable *in vivo* [21].

The high strength and stiffness of iron provide mechanical reliability that is unmatched by other biodegradable metals. However, for medical applications requiring fast bioresorption, iron alloys must be hybridized with more reactive elements or engineered at the surface. These modifications make them suitable for cardiovascular scaffolds where controlled degradation over 12–24 months is preferable to permanent implantation. [5]

Comparative Outlook and Biomedical Relevance

Every class of bio-degradable metallic alloy has its own merits and demerits. Although magnesium alloys are biocompatible with bone-like mechanical properties, they corrode fast. Zinc alloys provide moderate degradation rates and antimicrobial functionality, offering an excellent balance between mechanical performance and bioresorbability. Though iron alloys are stronger, they need improvements to degrade faster. Future studies will have to incorporate multi-component systems, which are based on the complementary strengths of the metals. Biodegradable metallic alloys are positively impacting the field of medical implants by achieving engineering accuracy that is acceptable to living organisms. By carefully controlling composition, microstructure, and corrosion behavior, these materials have the potential to create a new generation of temporary, bright, and biocompatible implants that heal as they disappear.

Design and Fabrication Strategies

The effective formation of biodegradable metallic implants requires the right design, processing, and structure. Every choice made in a design impacts the mechanical strength of the implant substrate, its degradation profile, and its biological properties. The ever-increasing demand for personalized and transient implants necessitates innovation in design and manufacturing strategies, prompting a rethinking of concepts, processing, and integration with living systems. [35]. The advanced manufacturing approaches focus on accuracy, biofunctionality, and adaptability, spanning the laboratory-clinic divide. The aim is for

the implants to degrade in sync with the tissue regeneration schedule, while still providing sufficient mechanical strength and biocompatibility throughout their lifetime [35; 36].

Making alloying an essential design strategy

Biodegradable metallic implants are developed through alloying, which involves adding specific elements to make predictable materials that corrode in a controlled manner. Metal alloying alters its electrochemical potential. Further, it influences the grain size, phase distribution, and solubility, among other factors. These modifications govern degradation and tissue interaction [37]. The introduction of calcium boosts bioactivity by supporting the osteogenesis process and bone-implant integration. Strontium (Sr) is known for its dual action of stimulating the formation of bone and reducing the metabolism of bone, while it also enhances corrosion stability [8]. In the same way, manganese (Mn) and zinc (Zn) are grain refiners that strengthen the microstructure and lower degradation rates [21]. Based on the research done on Magnesium-based systems, alloying calcium and zinc has proven to slow down rapid corrosion and improve mechanical reliability [14]. Mg-Ca-Zn ternary alloys exhibit enhanced osteogenic differentiation as compared to binary alloys due to the combined influence of the bioactive elements. In addition, cerium and yttrium have been increasingly studied for refining microstructures and enhancing the stability of passive films in biological media [38].

The art of alloying is a delicate balance, as too much addition of corrosion-modifying element(s) will result in slower degradation than desired. At the same time, too little will cause premature failure. To achieve this balance, we need a comprehensive understanding of biological response mechanisms and thermodynamic stabilization, ensuring that the rate of implant dissolution matches the rate of tissue healing [39].

Microstructure Engineering. The Heart of Performance Optimization

Besides the composition of biodegradable metals, their microstructural architecture determines their *in vivo* properties. Microstructure engineering is used for tailoring grain boundaries, dislocation densities, and secondary phase distributions for tuning corrosion kinetics and mechanical properties [4]. So, it is very necessary to control microstructural features accurately through thermomechanical processing (like extrusion, rolling, or heat treatment). Nano-grained alloys are the emerging trends with great potential. When you lower the grain size to the submicron scale, you will improve yield strength and corrosion uniformity, also due to lower galvanic potential differences. For example, in magnesium-based systems, ultrafine-grain refinement has been linked to improved surface passivation and decreased hydrogen evolution rates, making degradation more closely match bone healing timelines (40). Microstructure engineering is also significant for fatigue resistance, especially in the case of load-bearing implants such as screws and plates. By controlling the phase distributions, the crack initiation can be avoided. Whereas, grain orientation can be used to distribute the stresses efficiently. The relationship between its mechanical performance and corrosion in the body is central to clever microstructural design.

Fabrication via Powder Metallurgy. Controlling Precision and Porosity

According to [41]. Powder Metallurgy (PM) is one of the most effective fabrication methods for biodegradable metallic implants. It allows excellent control over composition, porosity, and grain size. The PM process, such as spark plasma sintering, hot pressing, or cold compaction, enables the near-net-shape production of complex geometries with reduced microstructural unevenness. Porosity can be introduced by the designer or controlled during powder consolidation. According to [37], the porosity of a calcium silicate with 021-069 levels aids cellular infiltration and nutrient exchange, in addition to providing adequate structural strength. Moreover, PM makes it possible to introduce gradients of composition and structure, thereby producing implants with site-specific degradation rates, such as faster resorption at the tissue-implant interface and slower rates at load-bearing cores. Powder metallurgy for magnesium and

zinc systems reduces the likelihood of oxidation during processing and promotes a more homogeneous distribution of the elements [36]. Additionally, the combination of PM with nano-additives or bioactive ceramic reinforcements (like hydroxyapatite or tricalcium phosphate) leads to hybrid systems with combined mechanical and biological advantages [35]. In the end, PM proves to be an adaptable, scalable, and affordable technique for the manufacture of biodegradable alloys with tailor-made porosity, composition, and surface topography to match mechanical behavior with physiological requirements.

Additive Manufacturing. The Frontier of Patient-Specific Implantation

Additive manufacturing, especially 3D printing, has changed biomedical engineering by providing designers greater freedom and customization for devices [21]. Through layer-by-layer fabrication, AM can create complex, patient-specific geometries that are not achievable with traditional manufacturing technologies. Biodegradable metals like magnesium and iron can be fabricated with intricate internal lattices, with optimized pores, and controlled density gradients through techniques such as selective laser melting (SLM) and electron beam melting (EBM) [39]. These designed porosities mimic the mechanical behavior of cancellous bone and promote vascularization and osteointegration by facilitating the diffusion of nutrients and invasion of tissues [4]. In addition, AM can regulate microstructure and grain orientation by controlling printing parameters (e.g., laser power, scan speed, cooling rate). This allows scientists to modify degradation profiles and mechanical anisotropy so that the implant behaves predictably in the body. Using processes powered by digital twins reinforces the general advantages of AM systems. AM can undergo precise alterations based on computer models that incorporate various pre-processing techniques. This type of prediction has helped with speed to market and clinical dependability.

AM represents the pinnacle of personalized medicine. Biodegradable implants can be customized for a particular patient both anatomically and functionally, while also being environmentally and economically sustainable.

Surface Engineering and Functional Coatings

The intrinsic properties of bulk alloy design control the material behavior of biodegradable metals, while surface engineering controls the biological behavior. The surface of the implant is an interface between synthetic material and living tissue, influencing cell adhesion, protein adsorption, and corrosion initiation [8]. Hydroxyapatite, calcium phosphate, and biopolymer coatings slow the dissolution of the metal substrate while simultaneously enhancing the osteogenic activity [23]. To ensure better tissue compatibility, the deposition of biodegradable polymer coating (e.g., polycaprolactone or chitosan) on magnesium alloy can reduce the hydrogen evolution and stabilize pH at the interface of the implant [42]. In the same fashion, micro-arc oxidation may create a ceramic-like surface layer that offers resistance to chloride attack, while maintaining a porosity that allows bone cells to anchor. Nanoscale surface texturing further fine-tunes implant-tissue interaction. The use of controlled roughness enhances protein adsorption and osteoblast attachment, leading to better osseointegration. Additionally, by incorporating bioactive molecules, such as peptides, antibiotics, or growth factors, into the implant surface, the implant can provide a therapeutic effect.

Surface Modification and Functionalization

Metallic alloys that are biodegradable in nature will be affected by their bulk composition and, critically, by their surface nature *in vivo*. The first interface that biological fluids and cells will encounter is the surface; thus, surface modification and functionalization are critical for improving corrosion resistance, enhancing cell attachment, and steering the biological response [37;21]. The primary purpose of surface engineering is to control degradation and encourage tissue integration, allowing the implants to offer temporary mechanical support without causing deleterious reactions.

Anodizing and plasma electrolytic oxidation

Anodization will create a thin and dense oxide film on a metal surface. It improves corrosion resistance. It modulates dissolution kinetics, too. To slow down the primary metal electrolyte contact of biodegradable magnesium and zinc alloys, and therefore the ensuing hydrogen evolution and rise in alkalinity near the implant, anodic films enriched with oxides or phosphates can help. PEO, or Plasma Electrolytic Oxidation, extends this technology by creating a micro-porous ceramic that tightly adheres to the substrate. The durability of PEO coatings was shown to release Ca^{2+} , Sr^{2+} , and Zn^{2+} ions that stimulate osteogenesis and angiogenesis [42] after implantation. The oxide layer that results, therefore, provides chemical and biological stability.

Coatings through sol-gel techniques and hybrid polymerizations

The sol-gel process enables the application of thin silica, titania, or hydroxyapatite coatings that are uniform and adherent. By delaying deterioration, these coatings also add functional groups for cell adhesion. On the other hand, polymer hybridization, where biodegradable polymers such as polycaprolactone (PCL), chitosan, or polylactic acid coat metallic substrates, provides an additional corrosion barrier and enhances the biocompatibility of the metallic substrate [34]. Drugs or growth factors can be encapsulated in hybrid coatings for localized therapeutic release, effectively turning a passive structural implant into an active biomedical device.

Ion Implantation Plus Functional Additives

Ion implantation is a technique that allows the introduction of beneficial species such as Ca, Sr, Ag, or N directly into the surface layer, without altering the bulk alloy. This method, which is based on diffusion, gradually refines the passive film, lowers surface free energy, and suppresses pitting corrosion. To prevent bacteria from causing any future harm, we add antibacterial agents for protection. Alloy surface modification as a whole can convert biodegradable alloys into multi-functional biomaterials with corrosion resistance, cell differentiation induction, and post-operative infection prevention.

Biocompatibility and Biological Interactions**Cellular Responses and Protein Adsorption**

The ability of biodegradable metal to function in the body and/or to have a therapeutic/biofunctional effect defines its biocompatibility. When a material is implanted in the body, its surface in contact with body fluids gets adsorbed by the proteins. The alloy's surface properties, including chemistry, roughness, and charge, affect how proteins will adhere to it. So, depending on the alloy, proteins like fibronectin or vitronectin may conform to it. Its further use is to help guide osteoblast or endothelial cell adhesion [4]. Cells tend to stick well to magnesium- and zinc-based implants because they let out essential biological ions. Excessive ion concentration, however, may disturb the osmotic balance or create local cytotoxicity, emphasizing the control on dissolution kinetics [39].

Inflammatory and Immune Reactions

The rate and chemistry of corrosion of biodegradable implants are closely related to the body's inflammatory reaction. Rapidly generating hydrogen or producing alkaline microenvironments can lead to macrophage activation and localized inflammation. On the other hand, slow degradation of materials that release low levels of Mg^{2+} or Zn^{2+} ions can promote the polarization of anti-inflammatory M2 macrophages. This process aids in tissue remodeling and enhances vascularization [35]. Histological assessment of the *in vivo* study shows that less chronic inflammation appears around optimized magnesium and zinc alloys. Modulated corrosion behaviour appears to contribute to immune-friendly materials [43].

Tissue integration and bone regeneration

The distinct characteristic of biodegradable implants is effective osseointegration. "As mentioned by [37], controlled corrosion allows mechanical load transfer while also releasing ionic species that enhance the proliferation and mineralization of bone cells." Calcium and strontium ions help in the differentiation of osteoblasts. Zinc ions support the synthesis of collagen and the activation of enzymes.

Research on animals shows that magnesium screws and plates can support strong bone regeneration. In fact, they can nearly all be replaced by natural bone within months [38]. The alignment of biochemical ion release with tissue healing kinetics is vital for the harmony of biodegradation and regeneration, according to the study.

Medical and Clinical Applications

Orthopedic Fixation Devices

Magnesium alloys have progressed the furthest along the clinic path among all biodegradable metals. Because their elastic modulus is very similar to that of cortical bone, which minimizes stress shielding and allows for physiological loading [4]. Bone fixation devices consisting of screws, plates, and intramedullary pins fabricated from Mg-Ca or Mg-Zn alloys show a controlled degradation rate matching bone consolidation period across 6–12 months [14]. Beneficial outcomes have been presented in the clinical trials treating orthopedic fixation devices made from magnesium in Europe and Asia [23]. The studies have shown total bio-resorption with successful bone healing and low inflammatory response. Seeing these results indicates that we shift from permanent to temporary self-eliminating implants.

Cardiovascular Stents

Zinc-based biodegradable stents have better mechanical properties and radiopacity than polymeric counterparts, making them viable alternatives. The moderate corrosion rate of zinc allows vascular remodeling to take place safely before the metal dissolves [35]. The addition of manganese or calcium in alloys may enhance endothelialization and prevent neointimal hyperplasia (36). Despite being mechanically strong, iron-based stents degrade quite slowly; therefore, measures such as micro-alloying with palladium or applying surface perforations have been devised to accelerate degradation [28].

Tissue engineering scaffolds and drug-eluting implants

Biodegradable metals and tissue engineering are combined to obtain a scaffold that provides mechanical support and biological signals. Additive manufacturing-generated porous magnesium and iron foams, able to imitate the architecture of cancellous bone, will aid in cell infiltration, nutrient diffusion, and vascularisation [39]. At the same time, drug-eluting bioresorbable implants are on the rise as the delivery vehicle for localized therapeutics, antibiotics, anti-inflammatory agents, or growth factors with structural support [42]. The slow dissolution of the metal matrix ensures a sustained release and overcomes the burst dose limitations of traditional polymeric carriers.

Regulatory and Translational Progress

The regulatory frameworks for biodegradable metallic implants are rapidly evolving, with several magnesium-based devices already approved for clinical use in orthopedic and cardiovascular applications [44]. ISO 10993 and ASTM F3268 now contain standardized assessments of biocompatibility and degradation. However, widespread use requires long-term post-implantation data and predictive corrosion models.

Challenges and Research Gaps

Biodegradable metallic alloys, while promising, face hurdles that prevent large-scale clinical use.

Corrosion and hydrogen evolution

The most significant limiting factor is the uncontrolled corrosion of magnesium systems. Rapid dissolution results in reduced mechanical stability of the matrix. It also induces the release of hydrogen gas, which gets trapped at the subcutaneous level, causing cavities or may delay the healing process [43]

Mechanical Integrity during Degradation

When implants disintegrate, load-bearing ability is lost. Alloy compositions may be designed (either through the gradation of microstructures or reinforcement phases) to ensure mechanical reliability during healing [39]. Models that connect loss of strength with corrosion rate have yet to be developed.

Limited Predictive Corrosion Models

Creating precise models for corrosion remains an unsolved issue because the physiological environment is dynamic and heterogeneous. There are new strategies that can predict degradation rates by using machine learning to analyze composition, microstructure, and surface treatment parameters. (41) Data-driven models speed clinical translation and material optimization.

Manufacturing and Scale-Up Barriers

Additive manufacturing and powder metallurgy can create designs with complex geometries but are hampered by scale, process, and cost (36). Having the same microstructure and porosity in the batches of processed particles is necessary for compliance and reproducibility.

Biocompatibility and Long-Term Safety

While short-term studies indicate good tolerance in both animals and humans, long-term biocompatibility requires further verification of systemic accumulation of degradation products. [35]. According to Santos-Coquillat *et al.*, standardized *in vitro* and *in vivo* protocols are needed to compare results.

Future Research Priorities

We'll need to integrate *in-situ* corrosion monitoring, multiscale simulation, and bio-realistic testing environments. Creating self-healing coatings, along with better alloys that can respond to biological feedback, could enhance implant durability.

Future Perspectives

We will see the emergence of next-generation biodegradable metallic alloys at the intersection of metals, data intelligence, and regenerative medicine.

AI-Driven Materials Discovery

Through a combination of AI and ML, one uses data-driven approaches to predict the optimal compositions, microstructures, and surface treatments that lead to desired degradation rates [39] with high-throughput computational screening followed by experimental validation, development cycles will be drastically reduced, enabling customized implant solutions.

Nanostructured and Biomimetic Coatings

Nanostructuring the surface through nano-patterning or biomimetic texturing improves cell adhesion and speeds up tissue regeneration [42] These surfaces that imitate natural extracellular matrix topographies promote osteoblast alignment and angiogenesis. The co-deposition of the antibacterial nanoparticles ensures infection resistance without any systemic toxicity.

Hybrid Polymer Metal Composites

New polymer-metal hybrids bring together rigid metallic frameworks and the controlled degradability of polymers. For instance, composites of Mg-PCL or Fe-chitosan attain gradual load transfer and tunable drug delivery profiles [37] The composites are linked to mechanical performance and biological suitability.

Integration with Regenerative Medicine and 3D Bioprinting

Coupling biodegradable metals with regenerative therapies, such as stem cell seeding and bioactive molecule incorporation, could be transformative [45] Simultaneously, 3D bioprinting not only constructs patient-specific scaffolds but also integrates vascular channels for holistic healing. We are entering an era with smart implants. These smart implants will send, receive, and respond to biological signals. In addition, the smart implants can adapt as required. Towards more innovative and sustainable biomedical substances.

Future research should also emphasize sustainability. The manufacturing processes of biodegradable implants, their designs, and lifecycle management should adhere to green manufacturing principles to reduce waste and energy consumption. New life-cycle analysis will ensure that drugs are environmentally friendly.

Conclusion

Metallic alloys that degrade in response to their bodily environment represent a paradigm shift in biomaterials engineering from passive permanent devices to active resorbing systems that participate therapeutically and assist in healing. The addition of bioactive agents provides interesting properties to the polymers, making them valuable for tissue engineering. Due to the progression of alloy design and surface modifications, these materials are moving quickly in the clinic. Overcoming the hurdles we currently face, particularly in corrosion, predictive modeling, and long-term biocompatibility, will require collaboration across chemistry, engineering, data science, and clinical domains. Far from being just materials, biodegradable metallic alloys are engineered living interfaces that can heal, regenerate, and disappear, leaving behind healed tissue and an improved quality of life.

References

- [1]. Zhu Y, Liu Y, Wu L, Yang Q. Global trends in the research of biodegradable biomedical magnesium-based materials: a bibliometric analysis. *Front Mater.* 2023;10:1265977. doi:10.3389/fmats.2023.1265977.
- [2]. Sort J. Special feature: permanent and long-term biodegradable biomaterials. *Appl Sci.* 2022;12(24):12874. doi:10.3390/app122412874.
- [3]. Yang H, Lin W, Zheng Y. Advances and perspective on the translational medicine of biodegradable metals. *Biomater Transl.* 2021;2(3):177-188. doi:10.12336/biomatertransl.2021.03.002.
- [4]. Thomas K, Zafar MN, Pitt WG, Hussein GA. Biodegradable magnesium alloys for biomedical implants: properties, challenges, and surface modifications with a focus on orthopedic fixation repair. *Appl Sci.* 2023;14(1):10. doi:10.3390/app14010010.
- [5]. Vinogradov A, Merson ED, Myagkikh P, Linderov M, Brilevsky A, Merson D. Attaining high functional performance in biodegradable Mg-alloys: an overview of challenges and prospects for the Mg-Zn-Ca system. *Materials.* 2023;16(3):1324. doi:10.3390/ma16031324.
- [6]. Zohdy KM, El-Sherif RM, El-Shamy AM. Effect of pH fluctuations on the biodegradability of nanocomposite Mg-alloy in simulated bodily fluids. *Chem Pap.* 2023;77(3):1317-1328. doi:10.1007/s11696-022-02544-y.
- [7]. Radwan-Pragłowska J, Legutko K, Janus Ł, Sierkowska-Byczek A, Kuźmiak K, Radwan-Pragłowska N. Electrochemical surface modification of fully biodegradable Mg-based biomaterials as a sustainable alternative to non-resorbable bone implants. *Appl Sci.* 2025;15(5):2492. doi:10.3390/app15052492.

- [8]. Taghipour S, Tahami FV, Allahverdizadeh A. Optimum design of a biodegradable implant for femoral shaft fracture fixation using finite element method. *Res Square*. 2024. doi:10.21203/rs.3.rs-4769010/v1.
- [9]. Liang W, Zhou C, Zhang H, Bai J, Jiang B, Jiang C, *et al*. Recent advances in 3D printing of biodegradable metals for orthopaedic applications. *J Biol Eng*. 2023;17(1):50. doi:10.1186/s13036-023-00371-7.
- [10]. Sort J. Special feature: permanent and long-term biodegradable biomaterials. *Appl Sci*. 2022;12(24):12874. doi:10.3390/app122412874.
- [11]. Yang H, Lin W, Zheng Y. Advances and perspective on the translational medicine of biodegradable metals. *Biomater Transl*. 2021;2(3):177-188. doi:10.12336/biomatertransl.2021.03.002.
- [12]. Shaikh MG, Kahwash F, Lu Z, Alkhreisat M, Mohammad A, Shyha I. Revolutionising orthopaedic implants: a comprehensive review on metal 3D printing with materials, design strategies, manufacturing technologies, and post-process machining advancements. *Int J Adv Manuf Technol*. 2024;134(3-4):1043-1072. doi:10.1007/s00170-024-14218-y.
- [13]. Ghazanfari H, Hasanizadeh S, Eskandarinezhad S, Hassani S, Sheibani M, Torkamani AD, *et al*. Recent progress in materials used towards corrosion protection of Mg and its alloys. *J Compos Compd*. 2020;2:205-214.
- [14]. Akbarzadeh F, Sarraf M, Ghomi ER, Kumar VV, Salehi M, Ramakrishna S, *et al*. A state-of-the-art review on recent advances in the fabrication and characteristics of magnesium-based alloys in biomedical applications. *J Magnes Alloys*. 2024;12(7):2569-2612. doi:10.1016/j.jma.2024.06.015.
- [15]. Macêdo TTS, Jesus ILA, Figueredo WN, Dordunoo D. Hypersensitivity reaction to metal: a bibliometric study. *SAGE Open Nurs*. 2022;8:23779608221132164. doi:10.1177/23779608221132164.
- [16]. Seetharaman S, Sankaranarayanan D, Gupta M. Magnesium-based temporary implants: potential, current status, applications, and challenges. *J Funct Biomater*. 2023;14(6):324. doi:10.3390/jfb14060324.
- [17]. Xu L, Liu X, Sun K, Fu R, Wang G. Corrosion behavior in magnesium-based alloys for biomedical applications. *Materials*. 2022;15(7):2613. doi:10.3390/ma15072613.
- [18]. Imani A, Rahimi E, Lekka M, Andreatta F, Magnan M, González-García Y, *et al*. Albumin protein impact on early-stage *in vitro* biodegradation of magnesium alloy (WE43). *ACS Appl Mater Interfaces*. 2024;16(1):1659-1670. doi:10.1021/acsami.3c12381.
- [19]. Moussa ME, Salem M, Hamid MA, Gomaa MH, Abd-Elwahed AHM, Ghayad IM, *et al*. Mechanical integrity and *in vitro* degradation behavior of Mg-Zn-Ca biodegradable alloy prepared by different casting technologies. *Int J Metalcast*. 2024;18(4):3062-3077. doi:10.1007/s40962-023-01229-w.
- [20]. Saberi A, Bakhsheshi-Rad HR, Abazari S, Ismail AF, Sharif S, Ramakrishna S, *et al*. A comprehensive review on surface modifications of biodegradable magnesium-based implant alloy: polymer coatings opportunities and challenges. *Coatings*. 2021;11(7):747. doi:10.3390/coatings11070747.
- [21]. Santos-Coquillat A, Martínez-Campos E, Sánchez H, Moreno L, Arrabal R, Mohedano M, *et al*. Hybrid functionalized coatings on metallic biomaterials for tissue engineering. *Surf Coat Technol*. 2021;422:127508. doi:10.1016/j.surfcoat.2021.127508.
- [22]. Almathami S, Venezuela J, Yang N, Wang Y, Mardina Z, Dargusch MS. Exploring the influence of biologically relevant ions on the corrosion behavior of biodegradable zinc in physiological fluids. *ACS Biomater Sci Eng*. 2023;9(5):2301-2313. doi:10.1021/acsbiomaterials.2c00901.

- [23]. Salaha ZFM, Abdullah NNAA, Chan KF, Gan H, Yusop MZM, Ramlee MH. Biodegradable orthopaedic implants: a systematic review of *in vitro* and *in vivo* evaluations of magnesium, iron, and zinc alloys. Results Eng. 2025;22:105746. doi:10.1016/j.rineng.2025.105746.
- [24]. Wei S, Ma J, Xu L, Gu X, Ma X. Biodegradable materials for bone defect repair. Mil Med Res. 2020;7(1):54. doi:10.1186/s40779-020-00280-6.
- [25]. Koushik TM, Miller C, Antunes E. Bone tissue engineering scaffolds: function of multi-material hierarchically structured scaffolds. Adv Healthc Mater. 2022;12(9):2202766. doi:10.1002/adhm.202202766.
- [26]. Raguraman S, Ulugun B, Ayodeji T, Chowdhury R, Griebel AJ, Weihs TP. Evaluating in-vitro corrosion testing of lean magnesium alloys: the critical role of degradation media composition, buffering, and volume. Res Square. 2024. doi:10.21203/rs.3.rs-5213784/v1.
- [27]. Cao B, Cao L, Kallmes DF. Degradation rate assessment of biodegradable magnesium alloys. Mater Sci Appl. 2024;15(8):245-256. doi:10.4236/msa.2024.158017.
- [28]. Ryu H, Seo M, Rogers JA. Bioresorbable metals for biomedical applications: from mechanical components to electronic devices. Adv Healthc Mater. 2021;10(17):2002236. doi:10.1002/adhm.202002236.
- [29]. Marvi-Mashhadi M, Ali W, Li M, González C, Llorca J. Simulation of corrosion and mechanical degradation of additively manufactured Mg scaffolds in simulated body fluid. J Mech Behav Biomed Mater. 2022;126:104881. doi:10.1016/j.jmbbm.2021.104881.
- [30]. Ezhilmaran V, Suya Prem Anand P, Kannan S, Sivashanmugam N, Jayakrishna K, Kalusuraman G. Review of bioresorbable AZ91, AZ31 and Mg-Zn-Ca implants and their manufacturing methods. Mater Sci Technol. 2023;39:901-925.
- [31]. Wang L, He J, Yu J, Arthanari S, Lee H, Zhang H, *et al.* Degradable magnesium corrosion control for implant applications. Materials. 2022;15(18):6197. doi:10.3390/ma15186197.
- [32]. Raguraman S, Ulugun B, Ayodeji T, Chowdhury R, Griebel AJ, Weihs TP. Evaluating in-vitro corrosion testing of lean magnesium alloys: the critical role of degradation media composition, buffering, and volume. Res Square. 2024. doi:10.21203/rs.3.rs-5213784/v1.
- [33]. Koushik TM, Miller C, Antunes E. Bone tissue engineering scaffolds: function of multi-material hierarchically structured scaffolds. Adv Healthc Mater. 2022;12(9):2202766. doi:10.1002/adhm.202202766.
- [34]. Salaha ZFM, Abdullah NNAA, Chan KF, Gan H, Yusop MZM, Ramlee MH. Biodegradable orthopaedic implants: a systematic review of *in vitro* and *in vivo* evaluations of magnesium, iron, and zinc alloys. Results Eng. 2025;22:105746. doi:10.1016/j.rineng.2025.105746.
- [35]. Liang W, Zhou C, Zhang H, Bai J, Jiang B, Jiang C, *et al.* Recent advances in 3D printing of biodegradable metals for orthopaedic applications. J Biol Eng. 2023;17(1):50. doi:10.1186/s13036-023-00371-7.
- [36]. Dargusch MS, Soro N, Demir AG, Venezuela J, Sun Q, Wang Y, *et al.* Optimising degradation and mechanical performance of additively manufactured biodegradable Fe-Mn scaffolds using design strategies based on triply periodic minimal surfaces. Smart Mater Med. 2024;5:127-138. doi:10.1016/j.smaim.2023.10.003.
- [37]. Hassan SF, Islam MT, Saheb N, Baig MMA. Magnesium for implants: a review on the effect of alloying elements on biocompatibility and properties. Materials. 2022;15(16):5669. doi:10.3390/ma15165669.

- [38]. Azadani MN, Zahedi SA, Bowoto OK, Oladapo BI. A review of current challenges and prospects of magnesium and its alloy for bone implant applications. *Prog Biomater.* 2022;11(1):1-15. doi:10.1007/s40204-022-00182-x.
- [39]. Kumar R, Mehrotra N, Pal K. Effect of hybrid nano rare earth reinforcement and hot rolling on mechanical, corrosion, and biocompatibility of biodegradable Mg implants. *Compos Struct.* 2025;349:119657. doi:10.1016/j.compstruct.2025.119657.
- [40]. Sharma SK, Gajević S, Sharma LK, Pradhan R, Miladinović S, Ašonja A, *et al.* Magnesium-titanium alloys: a promising solution for biodegradable biomedical implants. *Materials.* 2024;17(21):5157. doi:10.3390/ma17215157.
- [41]. Chandra G, Pandey A. Design approaches and challenges for biodegradable bone implants: a review. *Expert Rev Med Devices.* 2021;18(7):629-646. doi:10.1080/17434440.2021.1935875.
- [42]. Chen H, Wang Y, He L, Zhang X, Mei Y, Wu T, *et al.* Surface engineering of biodegradable magnesium alloys as orthopedic implant materials: recent developments and future prospects. *Coatings.* 2025;15(2):191. doi:10.3390/coatings15020191.
- [43]. Raguraman S, Ulugun B, Ayodeji T, Chowdhury R, Griebel AJ, Weihs TP. Evaluating in-vitro corrosion testing of lean magnesium alloys: the critical role of degradation media composition, buffering, and volume. *Res Square.* 2024. doi:10.21203/rs.3.rs-5213784/v1.
- [44]. Taghipour S, Tahami FV, Allahverdizadeh A. Optimum design of a biodegradable implant for femoral shaft fracture fixation using finite element method. *Res Square.* 2024. doi:10.21203/rs.3.rs-4769010/v1.
- [45]. Azadani MN, Zahedi SA, Bowoto OK, Oladapo BI. A review of current challenges and prospects of magnesium and its alloy for bone implant applications. *Prog Biomater.* 2022;11(1):1-15. doi:10.1007/s40204-022-00182-x.